

Postal address RISE IVF AB Box 104 SE-431 22 MÖLNDAL Tel +46 (0)31 706 60 00 Fax +46 (0)31 706 63 65		Visiting address Argongatan 30, SE- 431 53 MÖLNDAL Org. nr. 556053-1526 VAT no. SE556053-152601	
Client OOO EVROPLAST Ltd. Podolsk, pos. Selkhoztekhnika, Domodedovskoye shosse, bld.1/1 142116 Moscow Region, RUSSIA	Client's ref. no.		
	Contact person Olga Khrenova	Our ref. no.	5190015-13

Object

Determination of loss in thickness and hardness caused by fatigue according to IKEA's specification IOS-MAT-0076, version number AA-300587-6 (2016) for flexible polyurethane foam filling.

Test Material

1	Material producer:	OOO Evroplast Ltd
	Material description:	ST 2236 I
	Material batch number or equivalent:	392018120002 / 03.12.2018
	How and where sample was taken:	Foam block

The test material was received from the client 2018-12-27.

Procedure and results

Loss in thickness and hardness caused by fatigue was determined according to ISO 3385:2014 and IOS-MAT-0076, version no AA-300587-6.

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2019-01-30 – 02-01

Table 1. Loss in thickness and hardness caused by fatigue

Test material	Specimen	Δd	ΔH
		[%]	[%]
1	1	4.25	38.09
	2	4.29	38.20
	3	4.29	38.71
	Mean value	4.28	38.34
	Result	4.5	38


All results relate only to the material tested.

Mölndal, 2019-02-22

RISE IVF AB

Textile


Mary Rockström
Project leader, Foam Testing


Simonetta Granello
Test engineer