

Postal address RISE IVF AB Box 104 SE-431 22 MÖLNDAL Tfn +46 (0)31 706 60 00 Fax +46 (0)31 706 63		Visiting address Argongatan 30, SE- 431 53 MÖLNDAL Org. nr. 556053-1526 VAT no. SE556053-152601	
Client RIF Ametist Ltd. Vtoroy Pyatiletki Str. 140730 ROSHAL, RUSSIA		Client's ref. no.	
		Contact person Olesya Medvedeva	Our ref. no. 5181023-37

Object

Determination of loss in thickness and hardness caused by fatigue according to IKEA's specification IOS-MAT-0076, version number AA-300587-6 (2016) for flexible polyurethane foam filling.

Test Material

1	Material producer:	RIF Ametist
	Material description:	PU foam grade ST3542I
	Material batch number or equivalent:	3257 / production date 07.11.18
	How and where sample was taken:	Foam block

The test material was received from the client 2018-12-06.

Procedure and results

Loss in thickness and hardness caused by fatigue was determined according to ISO 3385:2014 and IOS-MAT-0076, version no AA-300587-6.

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2019-01-29 – 31


Table 1. Loss in thickness and hardness caused by fatigue

Test material	Specimen	Δd	ΔH
		[%]	[%]
1	1	1.87	25.21
	2	1.23	17.08
	3	1.85	25.22
	Mean value	1.65	22.50
	Result	1.5	23

All results relate only to the material tested.

Möln dal, 2019-02-05

RISE IVF AB



Mary Rockström
Project leader, Foam Testing



Simonetta Granello
Test engineer