

Postal address RISE IVF AB Box 104 SE-431 22 MÖLNDAL Tel +46 (0)31 706 60 00 Fax +46 (0)31 706 63 65	Visiting address Argongatan 30, SE- 431 53 MÖLNDAL Org. nr. 556053-1526 VAT no. SE556053-152601
Client Interfoam-Spb LLC pos. Voiskorovo, Tosnenskiy rayon 187033 LENINGRADSKAYA OBL. Russia	Client's ref. no.
	Contact person Olesya Medvedeva
	Our ref. no. 5190115-16

Object

Determination of loss in thickness and hardness caused by fatigue according to IKEA's specification IOS-MAT-0076, version number AA-300587-6 (2016) for flexible polyurethane foam filling.

Test Material

1	Material producer:	Interfoam-SPb
	Material description:	ST2536I
	Material batch number or equivalent:	11/128 , 27.11.18
	How and where sample was taken:	Foam block

The test material was received from the client 2019-02-06.

Procedure and results

Loss in thickness and hardness caused by fatigue was determined according to ISO 3385:2014 and IOS-MAT-0076, version no AA-300587-6.

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2019-02-26 – 28

Table 1. Loss in thickness and hardness caused by fatigue


Test material	Specimen	Δd	ΔH
		[%]	[%]
1	1	3.33	34.66
	2	3.36	34.68
	3	3.38	34.82
	Mean value	3.36	34.72
	Result	3.5	35

All results relate only to the material tested.


Mölndal, 2019-03-06

RISE IVF AB

Textile



Mary Rockström
Project leader, Foam Testing



Simonetta Granello
Test engineer