

Postal address RISE IVF AB Box 104 SE-431 22 MÖLNDAL Tfn +46 (0)31 706 60 00 Fax +46 (0)31 706 63 65		Visiting address Argongatan 30, SE- 431 53 MÖLNDAL Org. nr. 556053-1526 VAT no. SE556053-152601	
Client RIF Ametist Ltd. Vtoroy Pyatiletki Str. 140730 ROSHAL, RUSSIA	Client's ref. no.		
	Contact person Olesya Medvedeva	Our ref. no. 5181023-30	

Object

Determination of loss in thickness and hardness caused by fatigue according to IKEA's specification IOS-MAT-0076, version number AA-300587-6 (2016) for flexible polyurethane foam filling.

Test Material

1	Material producer:	RIF Ametist
	Material description:	PU foam grade S3530
	Material batch number or equivalent:	3023 / production date 14.10.18
	How and where sample was taken:	Foam block

The test material was received from the client 2018-12-06.

This report may not be reproduced other than in full, except with prior written approval of the issuing laboratory.
General terms and conditions for RISE IVF apply and may be ordered from RISE IVF.

Procedure and results

Loss in thickness and hardness caused by fatigue was determined according to ISO 3385:2014 and IOS-MAT-0076, version no AA-300587-6.

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2019-01-18 – 23


Table 1. Loss in thickness and hardness caused by fatigue

Test material	Specimen	Δd	ΔH
		[%]	[%]
1	1	2.71	24.08
	2	2.46	25.27
	3	2.33	24.57
	Mean value	2.50	24.64
	Result	2.5	25

All results relate only to the material tested.

Mölndal, 2019-01-28

RISE IVF AB


Mary Rockström
Project leader, Foam Testing


Monica Cristea
Test engineer