

Postal address Swerea IVF AB Box 104 SE-431 22 MÖLNDAL Tfn +46 (0)31 706 60 00 Fax +46 (0)31 706 63		Visiting address Argongatan 30, SE- 431 53 MÖLNDAL Org. nr. 556053-1526 VAT no. SE556053-152601	
Client RIF Ametist Ltd. Vtoroy Pyatiletki Str. 140730 ROSHAL, RUSSIA		Client's ref. no.	
		Contact person Olesya Medvedeva	Our ref. no. 5070132-36

Object

Determination of loss in thickness and hardness caused by fatigue according to IKEA specification IOS-MAT-0076, version no AA-300587-6.

Test Material

1	Material producer:	RIF Ametist
	Material description:	S2525
	Material batch number / production date:	429 / 05/02/17

The test material was received from the client 2017-02-21

Procedure and results

Loss in thickness and hardness caused by fatigue was determined according to according to ISO 3385:2014 and IOS-MAT-0076, version no AA-300587-6.

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2017-04-12 – 04-19


Table 1. Loss in thickness and hardness caused by fatigue

Test material	Specimen	Δd	ΔH
		[%]	[%]
1	1	2.58	27.93
	2	2.42	25.09
	3	2.28	27.50
	Mean value	2.42	26.84
	Result	2.5	27


All results relate only to the material tested.

Möln dal, 2017-04-19

Swerea IVF



Desiré Rex
Project leader, Foam Testing



Simonetta Granello
Test engineer

This report may not be reproduced other than in full, except with prior written approval of the issuing laboratory. General terms and conditions for Swerea IVF apply and are available on www.swereaivf.se or may be ordered from Swerea IVF.